



Technical Data Sheet – PA6 BCF Yarn

POLYAMIDE-6 BCF YARN – HS CODE 5402 3200			
Most commonly used for production of Loop Pile Tufted Printed Carpets			
<u>Property</u>	<u>Value</u>	<u>Unit</u>	<u>Tolerance</u>
Filament cross section	Tri-lobal	NA	NA
Melting point	210 - 220	°C	NA
Specific gravity of PP	1,13 – 1,15	g/cm ³	NA
Yarn count (dtex) with no. of fils	1000/68f	Dtex/Nos.	+/- 3%
Tenacity	2,7	gms/den	+/- 5%
Elongation at break	30	%	+/- 5%
Spin Finish	0.6 to 0.7	%	+/- 0.1
Entanglement	25 – 30	Nips/metre	+/- 5
UV – Stabilisation	On demand	Hours	min. 600
Lustre	Super Bright	NA	NA
Winding	Cross-wound on paper tubes	NA	NA
Net Weight of bobbin	3,40	Kgs	+/- 3%
Packing	680kgs/pallet 200 bobbins/pallet About 13.6tons/40FCL HQ	NA	NA

Genesis Synthetics Pvt. Ltd.

A-801, Signature 2, Sarkhej-Sanand Circle, Ahmedabad-382 210, Gujarat, India.

T.: +91-79-2693 7386 • E.: ravi@bcfyarn.com • W.: www.bcfyarn.com

